



Lipidure®-CM5206 Powder

CERTIFICATE OF ANALYSIS

Date APR. 24, 2014

Trade name : Lipidure-CM5206

Lot # 130521

Appearance White powder or small lump

Hiroyuki Nomura
Signature of QC Manager

Property	Specification	Analysis Result
Identification / IR Spectrum	Adaptation	Adaptation
Viscosity (25°C) (cSt)	30 - 120	54
Copolymerization ratio of MPC (mol%)	25 - 35	30

Ordering Details

Code	Description	Pack	Storage
AMS.52000011GB1G	Lipidure-CM5206 (White powder), 1g	1 g	Room Temperature
AMS.52000012GB10G	Lipidure-CM5206 (White powder), 10g	10 g	Room Temperature
AMS.52000012GB100G	Lipidure-CM5206 (White powder), 100g	100 g	Room Temperature e

Lipidure-Coated plates and dishes also available up to 384-well format – see

www.amsbio.com/Lipidure-Coat.aspx

AMSBIO | www.amsbio.com | info@amsbio.com


 **UK & Rest of the World**
184 Park Drive, Milton Park
Abingdon OX14 4SE, UK
T: +44 (0)1235 828 200
F: +44 (0) 1235 820 482

 **North America**
1035 Cambridge Street,
Cambridge, MA 02141
T: +1 (617) 945-5033 or
T: +1 (800) 987-0985
F: +1 (617) 945-8218

 **Germany**
Bockenheimer Landstr. 17/19
60325 Frankfurt/Main
T: +49 (0) 69 779099
F: +49 (0) 69 13376880

 **Switzerland**
Centro Nord-Sud 2E
CH-6934 Bioggio-Lugano
T: +41(0) 91 604 55 22
F: +41(0) 91 605 17 85

How Does Lipidure® -COAT Work?



- 1. Low-adhesion surface promotes cell aggregation & spheroid formation.
- 2. Uses MPC Polymer: a biocompatible polymer containing Phosphorylcholine (which is found in cell membranes).
- 3. Completely synthetic, containing no substances of biological origin.

Coating Protocol:


1. Dissolve Lipidure®-CM in ethanol and prepare a 0.5wt% ethanol solution.
2. Dip the base material into the coating solution for 1 min
(or place Lipidure solution on substrate and coat evenly)
3. Dry the coated material at room temperature or one hour at 50°C.

Once reconstituted, the solution can be stored at room temperature. It is best to reconstitute in a glass container (rather than plastic), as some plastic might bleed from plastic container into Lipidure solution.

Lipidure®-CM can be coated on the following substrates:

Plastics (PET, PMMA, PSt, PU, PC, PE, PP)
Glass, Ceramics and Metals (SUS, titanium, gold)

Relationship between number of times coating was applied and thickness of coating film



Lipidure is a registered trademark of NOF Corporation

AMSBIO | www.amsbio.com | info@amsbio.com